

TECHNICAL DATA SHEET SMARTBOND FLEX GOLD C2TS1 Flexible Tile Adhesive

PRODUCT DESCRIPTION:

SMARTBOND FLEX GOLD FLEXIBLE TILE ADHESIVE C2TS1

conforms to PNS ISO 13007-1:2014 type C2TS1 with Heavy-duty adhesion, Slip-Resistance, and Standard Flexibility for permanent bonding of tiles such as porcelain, marble, granite, and natural stones, on indoor and outdoor floors or walls.

It is a lightweight, flexible tile adhesive especially formulated using flexible polymers, lightweight filler, and special additives to provide easy mixing, excellent workability, low dust, and no slump or shrinkage while maintaining optimum strength and flexibility.

It has flexible characteristics that can absorb different stresses, such as concrete shrinkage and thermal expansion. It has a slipresistant capability which prevents the tile from slipping when installed on the vertical surfaces of walls.

It is carefully developed to give an extended open time/pot life, ideal for longer working time requirements. It's low dust emissions bring health and safety advantages. Its unique water retention technology is the key to preventing tile debonding.

Tile Adhesive Classification According to Philippine National Standard following ISO 13007-1:2014

C = Adhesion	S = Flexibility	T = Slip Resistant	
C1 = Bonding strength 0.5 N/mm ²	S1 = deformability ≥ 2.5 mm but < 5mm	Slip resistance vertical application	
C2 = Bonding strength 1.0 N/mm ²	S2 = deformability ≥ 5.0 mm		

CUSTOMER BENEFITS:

- Endures structural movement
- Prevents tile de-bonding
- Reduces cost of transport
- Follows European and Philippine standard
- Environmentally friendly

SMARTBOILD RECOMMENDATION TABLE				
APPLICATION	C1TS1	C2TS1	C2TS2	
SIZE OF TILES	30x30cm & below the size of tiles	60x60cm & below the size of tiles	60x90cm & above the size of tiles	
TYPE OF TILES	Ceramic & earthenware	Porcelain, mosaic, marble, granite, and most types of tiles	Porcelain, marble, granite, and most types of tiles	

All floor-leve

application

Floor and wal

application

or and outdo

All floor-leve

application

Indoor and outdoo

Floor and wall

application

All floor-leve

application

Indoor and outdoor

Floor and wall

application

SMADTROND DECOMMENDATION TABLE

INSTRUCTION FOR USE

PREPARATION

FLOOR

ELEVATION

AREA OF

APPLICATION

All substrates must be clean, dry, and strong enough to support the weight of the tiles and adhesive. Remove all dust, dirt, oil, grease, paints, and other contaminants that may affect adhesion. New render/screed surfaces must be allowed to cure for at least 7 days while new concrete must have cured for 6 weeks.

MIXING

Pour 6.8 - 7.2 liters of water into a clean container. Slowly add 0.015cbm of tile adhesive and mix with a slow-speed mechanical mixer until a homogenous and lump-free paste is obtained. Allow the mix to stand for 3 minutes and re-stir before use.

APPLICATION

The tile adhesive is spread on the substrate to a uniform thickness. The correct notched trowel size to use will depend on the type and size of the tiles.

Lay the tiles onto the adhesive and ensure that a firm pressure is applied to achieve good contact with the adhesive.

For large format size of tiles (60cm x 90cm and up) back-buttering is recommended according to ANSI and TCNA guidelines to increase the bond strength of tile adhesive.

Only apply to areas which can be tiled in the adhesive's open wet time.

Careful checks have to be made to ensure that skinning does not occur on the surface of the adhesive before laying the tiles. If skinning has occurred, rework the adhesive before laying the tiles.

The adhesive will remain workable for 90 minutes, has an open time of 20-30 minutes and can be grouted after 24 hours after laying the tiles.

SMARTBOND FLEX GOLD 02.24 Version 0.0





TECHNICAL DATA SHEET SMARTBOND FLEX GOLD C2TS1 Flexible Tile Adhesive

CLEANING

Remove excess adhesive with a damp cloth before the material has set. After setting, cleaning becomes very difficult but can usually be helped by mechanical means. Once the tiling is complete, do not disturb for at least 4 hours. Wait 24 hours after grouting before opening the area to dry service and 7 days for wet service.

Note: Setting time, open time, and pot life of the adhesive are affected by temperature. In cold weather, setting time will be slower, and in warm weather setting time will be faster. Do not apply in temperatures above 35 °C.

COVERAGE

0.015cbm bag of **SMARTBOND FLEX GOLD FLEXIBLE TILE ADHESIVE C2TS1** mixed with 6.8 to 7.2 liters of water will cover 5 sqm at 3 mm thickness.

PACKAGING

SMARTBOND FLEX GOLD FLEXIBLE TILE ADHESIVE C2TS1 is supplied in 0.015cbm bag

STORAGE

SMARTBOND FLEX GOLD FLEXIBLE TILE ADHESIVE C2TS1

flexible tile adhesive has a shelf life of 12 months if maintained in dry storage conditions in unopened bags.

HEALTH & SAFETY

Gloves should be worn during application. Care should be taken to avoid inhalation of dust and contact with eyes.

Refer to the Safety Data Sheet (SDS) for complete safety information on handling the product.

WARRANTY AND DISCLAIMERS

The information provided in this technical data sheet is based on our best knowledge and testing methods at the time of publication. While we believe the information is accurate and reliable, it is presented without any express or implied guarantee, warranty, or responsibility. Any use of the product outside of specifications or improper storage or installation voids any warranty. Users are encouraged to conduct their own testing to assess product suitability. Always consult the product's safety data sheet (SDS) for safety guidelines and follow recommended precautions. We reserve the right to update this data sheet without notice, users should ensure they have the latest information.

SMARTBOND FLEX GOLD 02.24 Version 0.0

